



Jagdamba Paper Corporation

Product : Fluting Medium Paper Kraft



KRAFT PAPER- FM
MUMBAI, MAHARASTRA

PRODUCT PROPERTIES INFORMATION OF FLUTING MEDIUM

S.No.	GSM	CMT	THICKNESS	RCT MD/ CD	RCT MD/ CD	COBB (60 Sec)	MOISTURE
		(30Min)	(micron)	(Kn/m)	(Kg/f)	T/B	%
1	115	0.60	152	1.23/1.08	17/13	35/40	7-7.5
2	125	0.70	167	1.29/1.09	19/14	35/40	7-7.5
3	140	0.85	182	1.38/1.10	21/17	35/40	7-7.5
4	150	0.95	192	1.44/1.20	22/19	35/40	7-7.5
5	180	1.15	235	2.05/1.60	32/25	35/40	7-7.5
6	200	2.21	266	2.25/1.75	35/27	35/40	7-7.5

TAPPI STD. TOLERANCE:- 1.RCT (+/- 0.322KN/m), 2.PLY BOND (+/- 5%), 3.CALIPER (+/- 4%), 4.MOISTURE (+/-5%)

TESTING CONDITION -TEM-26 °C (+/- 1°C), RELATIVE HUMIDITY 50%(+/-5%)

TAPPI - TECHNICAL ASSOCIATION OF PULP AND PAPER INDUSTRY