



Jagdamba Paper Corporation

Product : Kraft Paper - TL



KRAFT PAPER - TL

MUMBAI, MAHARASTRA - INDIA

PRODUCT PROPERTIES INFORMATION OF TEST LINER

S.No.	GSM	BR	THICKNES	RCT MD/ CD	RCT MD/ CD	COBB (60 Sec)	MOISTURE
		(min)	(micron)	(Kn/m)	(Kg/f)	T/B	%
1	130	3.1	182	1.38/0.9	21/14	35/40	7-7.5
2	140	3.21	192	1.44/1.31	22/20	35/40	7-7.5
3	150	3.32	235	1.92/1.37	30/21	35/40	7-7.5
4	160	3.39	225	2.25/1.61	35/25	35/40	7-7.5
5	180	3.72	335	2.80/1.92	43/30	35/40	7-7.5
6	200	4.09	368	3.15/2.23	49/34	35/40	7-7.5

TAPPI STD. TOLERANCE:- 1.RCT (+/- 0.322KN/m), 2.PLY BOND (+/- 5%), 3.CALIPER (+/- 4%), 4.MOISTURE (+/-5%)

TESTING CONDITION -TEM-26 °C (+/- 1°C), RELATIVE HUMIDITY 50%(+/-5%)

TAPPI - TECHNICAL ASSOCIATION OF PULP AND PAPER INDUSTRY