



Jagdamba Paper Corporation

Product : White Top Liner

Quality: White Top Liner

GSM: 180

Properties		UOM	Min	Max	Avg.
Grammage		g/m ²	174	184	182
Caliper		micron	210	224	220
Bulk		cc/g	1.20	1.22	1.21
Stiffness	MD	g.cm	29	33	31
	CD	g.cm	11	16	14
	GM	g.cm	18	23	21
Stiffness ratio	MD / CD		2.64	2.06	2.21
Plybond	CD	Ft. LB in thousandths	76	82	79
Cobb 60	TS	gsm	34	38	36
	BS	gsm	35	39	37
Moisture	Lab	%	6.1	6.6	6.3
Gloss		%	31.0	34.0	32.0
Roughness	TS	μm	2.5	2.8	2.7
Brightness	TS	%	73.8	74.5	74.2